PRO-COM®
Interior/Exterior Multi-Purpose Primer
PCMP00

APPLY A HIGHER STANDARD®

PRO-COM® Multi-Purpose Primer is an interior/exterior, ultra-low VOC, multi-surface primer, ideal for commercial and multifamily properties. It provides good adhesion to properly prepared drywall, wood, and masonry, as well as hard-to-stick surfaces, such as aged alkyd, aluminum, and galvanized metal.

PRODUCT INFORMATION

SOLVENT TYPE: Waterborne | **RESIN TYPE:** Copolymer

FINISH (ASTM D 523): 1–7% on a 60º meter

COLORS: White. **PRO-COM® Multi-Purpose Primer** may be tinted with up to 2 fl. oz. of Dunn-Edwards ZTC Zero VOC colorant per gallon.

VISCOSITY@77ºF/25ºC (ASTM D 562): 88–95 KU

MAXIMUM VOC CONTENT 25 g/L (by ASTM Test Method D 6886)	**MAXIMUM RAVOC** (Reactivity-Adjusted VOC) 20 g/L
SOLIDS BY VOLUME (ASTM D 2697) 33.1% ± 2%	**SOLIDS BY WEIGHT** 44.8 ± 2%

WEIGHT PER GALLON (ASTM D 1475)**:** 10.41 lbs.

COMPOSITION BY WEIGHT

Pigment–30.0%		**Vehicle–70.0%**	
*Prime pigments	8.9	Resin solids	12.8
Reinforcing pigments	21.1	Water & additives	57.2

**Prime pigments include titanium dioxide (TiO^2), plus all other pigments directly adding to the hiding power of this paint.*

RECOMMENDED FILM THICKNESS PER COAT
Wet: 4.5 mils Dry: 1.5 mils

PRACTICAL COVERAGE PER COAT AT RECOMMENDED DRY FILM THICKNESS
Approximately 300-350 sq. ft. per gallon, depending on surface conditions and application techniques.

THINNING RECOMMENDATION: This coating is intended to be applied without thinning or diluting under normal environmental and application conditions. If necessary to maintain good workability, add up to 1/4 pint (4 fl. oz.) of clean water per gallon of coating.

AVERAGE DRY TIME@77ºF/25ºC (ASTM D 1640)
To touch: 1–2 hours Recoat: 2–4 hours
Dry times and recoat times are temperature, humidity and film thickness dependent.

APPLICATION EQUIPMENT: Airless spray

AIRLESS SPRAY	BRUSH	ROLLER
PRESSURE: 1800-2500 psi **TIP:** .013”-.017”	Nylon/Polyester	Smooth Surfaces: ¼” - ⅜” nap Semi-Smooth Surfaces: ⅜” - ½” nap

PACKAGING: One-gallon, five-gallon containers

STORAGE: Store in a dry area. Protect from freezing. Protect from temperatures above 110ºF for extended periods of time. Extreme temperatures may cause paint to become unusable. See *Paint Storage Best Practices* Technical Bulletin at dunnedwards.com for more information.

CLEANUP: Warm, soapy water

DISPOSAL: For information on local options to dispose of unwanted leftover paint, call Dunn-Edwards Customer Service at 1-888-DEPAINT or visit www.dunnedwards.com. **Do not mix with other products**.

CONFORMS TO:	
• ARB 2007/2020 SCM & CALGreen 2022 • CA Section 01350 • LEED v4/4.1 • SCAQMD Rule 1113	• CA Extended Producer Responsibility • MIR, HPD • FDA Guidelines for Coatings

SAFETY DATA SHEET: Available at www.dunnedwards.com

SURFACE PREPARATION: All surfaces must be cured, clean, dry, and free from dirt, dust, rust, stains, grease, oil, mildew, wax, efflorescence, bond-breakers, and other contaminants. Remove all loose, peeling, or chalky paint by sanding, scraping, or other appropriate methods. Repair all cracks, holes, and other surface imperfections with a suitable patching material. Repaired surfaces should then be sanded smooth and dusted clean. Glossy surfaces should be dulled to provide a roughened surface for good adhesion.

SPECIAL INSTRUCTIONS

- **CAUTION!** Scraping or sanding surfaces of older buildings (especially pre-1978) may release dust containing lead or asbestos. EXPOSURE TO LEAD OR ASBESTOS CAN BE VERY HAZARDOUS TO YOUR HEALTH. Wear a NIOSH-approved N100 particulate filter mask to avoid breathing dust. Use a HEPA vacuum for cleanup, and finish by water-washing all surfaces. For more information, see Dunn-Edwards brochure on “Surface Preparation Safety” or call U.S. EPA’s lead hotline at 1-800-424-LEAD, or visit www.epa.gov/lead or / asbestos, or contact your state or local Health Agency.
- This product can neither cause nor prevent or cure the growth of mold, mildew, or other forms of fungus. Excessive moisture and inadequate ventilation are the main conditions that promote their growth. Correct any such conditions before painting.
- **PRO-COM® Multi-Purpose Primer (PCMP00)** seals and blocks out most household stains, such as crayon, pencil, ink, and felt marker. After priming stained areas, test that the stain has been sealed by applying the topcoat to a small area. More than one coat may be necessary on severe stains. **PRO-COM® Multi-Purpose Primer (PCMP00)** may block minor dried water stains, however, a stain-blocking primer, such as BLOCK-IT, is recommended.
- Galvanized metal must be cleaned with a solvent or a water-soluble degreasing cleaner to remove all oils prior to etching. Change wiping material and cleaning solution frequently so the oils are removed from the surface, not just spread around. The surface should then be treated with an etching solution to promote proper adhesion of coatings.
- **PRO-COM® Multi-Purpose Primer (PCMP00)** can be used on bare ferrous metal surfaces (interior only) provided that they are free of rust, mill scale, and other contaminants. Before any surface preparation is attempted, oil and grease must be removed by employing SSPC-SP11 Power Tool Cleaning to Bare Metal to remove mill scale, rust, or other contaminants and to leave a roughened surface.
- Before applying over previously painted surfaces, **PRO-COM® Multi-Purpose Primer (PCMP00)** should be tested for adhesion and compatibility.
- On Level 4 and 5 Drywall Finishes, thin **PRO-COM® Multi-Purpose Primer (PCMP00)** with 10% of clean water (3/4 pint per gallon/1/2 gallon per 5-gallon) for best penetration.
- Allow to dry overnight before applying solvent-based epoxy and urethane topcoats - *INTERIOR ONLY*.
- Do not apply when the air or surface temperature is below 50ºF.

PRO-COM®
Interior/Exterior Multi-Purpose Primer
PCMP00

APPLY A HIGHER STANDARD®

PRODUCT INFORMATION

PRIMERS

WALLBOARD & MASONRY: PRO-COM® Multi-Purpose Primer can be applied on surfaces with a pH of up to 13.

Drywall:
Stucco:
Concrete:
Brick:
→ **PRO-COM® Multi-Purpose Primer (PCMP00)**

WOOD-INTERIOR

Doors, trim
→ **PRO-COM® Multi-Purpose Primer (PCMP00)** or **DECOPRIME® (DCPR00)**

WOOD-EXTERIOR

Trim, sash:
T1-11 siding:
→ **PRO-COM® Multi-Purpose Primer (PCMP00)** or **EZ-PRIME® Select (EZPR00)**

SYNTHETIC WOOD

Masonite:
Hardboard:
→ **PRO-COM® Multi-Purpose Primer (PCMP00)**

METAL

Ferrous:
→ **BLOC-RUST® Premium (BRPR00), ENDURAPRIME® Metal Primer (ENPR00)** or **PRO-COM® Multi-Purpose Primer (PCMP00) –** INTERIOR ONLY

Non-ferrous:
→ **ENDURAPRIME® Galvanized Metal Primer (ENGM00) [Formerly ULTRASHIELD® Galvanized Metal Primer (ULGM00)], BLOC-RUST® Premium (BRPR00)** or **SUPER-LOC® Premium (SLPR00)**

Galvanized steel:
→ **ENDURAPRIME® Galvanized Metal Primer (ENGM00) [Formerly ULTRASHIELD® Galvanized Metal Primer (ULGM00)]** or ***ULTRA-GRIP® Premium (UGPR00)**

OTHER SURFACES

Fiberglass:
Plastic:
→ **PRO-COM® Multi-Purpose Primer (PCMP00) –** INTERIOR ONLY

**for incidental use on galvanized*

HEALTH & SAFETY CAUTIONS! INHALATION OF SPRAY MIST OR SANDING DUST MAY BE HARMFUL. Use only with adequate ventilation. Avoid breathing vapors, spray mist and sanding dust. Wear NIOSH-approved N100 particulate filter mask when spraying or sanding. Avoid contact with skin and eyes. Do not ingest. Close container after each use. **FIRST AID:** If swallowed, immediately give 1 or 2 glasses of water to drink – for emergency information, call 1-800-222-1222. If having difficulty breathing, move to fresh air. For eye contact, immediately flush with water for 15 minutes. For skin contact, wash thoroughly with soap and water.

• KEEP OUT OF REACH OF CHILDREN •

Ingredient (CAS #): Water (7732-18-5); Copolymer Resin (Proprietary); Talc, Non-Asbestos (14807-96-6); Kaolin Clay (1332-58-7); Titanium Dioxide (13463-67-7).

⚠ **WARNING:** Cancer and Reproductive Harm – www.P65Warnings.ca.gov