



**CERAMIC COAT
LOW ODOR
STAIN RESISTANT EGGSHELL
1600 LINE**

Type	Sheen	Spread Rate	Recommended Application	Thinner	Clean Up	DRY TIME		
						Tack Free	Re-coat	Cure
100% Acrylic	Eggshell	Up to 400 Sq Ft Per Gallon	Brush, Roller, Pad or Airless Spray	Clean Water	Warm Soapy Water	30 Minutes	4 Hours	30 Days
PRODUCT NAME: 1600 LINE CERAMIC COAT LOW ODOR STAIN RESISTANT EGGSHELL		A top grade interior, 100% Acrylic, Low Odor, Eggshell Wall Paint, formulated with ceramic spheres to impart excellent stain resistance properties. Finger prints, soil, grease, and many other stains wash off with mild soap and water without harming the film. This product complies with LEED Green Building Rating System GS-11 for interior non-flat paints.						
WHERE TO USE:		Drywall Plaster Wood Metal Masonry This eggshell latex wall paint is a very low odor, low VOC product, making it perfect for hospitals, schools, homes or any area where odor is a concern. Available in over 1400 colors.						
SURFACE PREPARATION:		New Work: The surface to be coated must be clean and free of dust, grease, wax, rust, oil, and bleeding stains. Priming: Drywall – #50 Acrylic Primer Sealer or 5790. Plaster – For best results use No. 50 Acrylic Primer Sealer or 5790. Wood – Alkyd Primer Undercoat, #37-11, #50 or #0590. Ferrous Metal – Rust inhibiting metal primer such as #35-11, #2090 or #0560. Non-Ferrous Metal – PermaBond #100-10. Galvanized – Acrylic Primer #36-11 or #100-10. Masonry – Use Primer Sealer 43-10 or 48-11. To fill porous block use 946-11 Latex Block Filler or 529-11 Block Filler. Repaint Work: On previously painted surfaces in good repair, no priming is generally necessary. On glossy surfaces, remove the sheen with sandpaper or steel wool. Patch holes or cracks with appropriate filler. Spot prime bare areas with indicated primer. Remove any oil, chalk, dirt, wax or dust prior to re-coating. Any loose or flaking paint should be removed and the edges feather sanded to produce a smooth, uniform surface.						
APPLICATION:		Stir product with a circular, lifting motion to disperse into a homogenous liquid. To achieve proper results a quality 3/8" nap roller cover is required when using products containing ceramic microspheres. Brush – Nylon or polyester filament. Airless Spray – Tip at atomization pressures will vary with type of equipment, viscosity and temperature. An orifice of .017 - .019 will provide the most satisfactory spray pattern. Best results are more likely obtained by using quality application tools. Do not apply directly over chalky surfaces or bleeding stains.						
NOTE: Formulated without mercury or lead.								

RESIN:	100% Acrylic
SOLIDS:	Weight – 52.5 Volume – 36.0
WEIGHT PER GALLON:	11.10 lbs.
VISCOSITY:	90 – 95 (Krebs Units)
SPECULAR GLOSS:	6 – 10% @ 60 degrees
RECOMMENDED FILM THICKNESS:	Wet – 3.5 to 5.0 mils Dry – 1.3 to 1.5 mils
VOC – VOS STATEMENT:	This product contains less than .84 lbs per gallon or 100 G.P.L.
CAUTIONS:	CAUTION! Do not take internally. Close container after each use. KEEP OUT OF REACH OF CHILDREN. KEEP FROM FREEZING.

REV. 03/2016

