EZ-PRIME® Select
Exterior Wood Primer
EZSL00

APPLY A HIGHER STANDARD®

COPOLYMER™ | EG-FREE Formulated without Ethylene Glycol or any other TAC/HAP chemical | green wise® CERTIFIED BY COATINGS RESEARCH GROUP INCORPORATED

≤ 50 g/L VOC**

EZ-PRIME® Select is an exterior acrylic primer that provides good enamel holdout and tannin stain resistance on woods such as redwood and cedar, which are subject to stain bleeding. **EZ-PRIME Select** is also recommended on exterior plywood and T1-11 siding.

PRODUCT INFORMATION

SOLVENT TYPE: Waterborne | **RESIN TYPE:** Copolymer

FINISH (ASTM D 523): 5–15% on a 60º meter

COLORS: White. White. **EZ-PRIME Select** may be tinted with up to 2 fl. oz. of Dunn- Edwards ZTC Zero VOC colorant per gallon.

VISCOSITY@77ºF/25ºC (ASTM D 562): 90–100 KU

MAXIMUM VOC CONTENT	**MAXIMUM RAVOC** (Reactivity-Adjusted VOC)
50 g/L (as supplied)	25 g/L

SOLIDS BY VOLUME (ASTM D 2697)	**SOLIDS BY WEIGHT**
38.1% ± 2%	52.0 ± 2%

WEIGHT PER GALLON (ASTM D 1475)**:** 10.73 lbs.

COMPOSITION BY WEIGHT

Pigment–29.4%		**Vehicle–70.6%**	
*Prime pigments	14.1	Resin solids	20.9
Reinforcing pigments	15.3	Water & additives	49.7

**Prime pigments include all pigments directly adding to the hiding power of this paint.*

RECOMMENDED FILM THICKNESS PER COAT
Wet: 5.2 mils Dry: 2.0 mils

PERFORMANCE SPECIFICATION
Mandrel Bend Results: Pass | **ASTM D 522-B (No Cracking over 1/4" mandrel)**
Biological Growth Results: Pass (rated 8 and above) | **ASTM D 3273**
Adhesion Results: Pass 100% | **ASTM D3359 (Birch)**

PRACTICAL COVERAGE PER COAT AT RECOMMENDED DRY FILM THICKNESS
Approximately 250-325 sq. ft. per gallon, depending on surface conditions and application techniques.

THINNING RECOMMENDATION: This coating is intended to be applied without thinning or diluting under normal environmental and application conditions. If necessary to maintain good workability, add up to 1/4 pint (4 fl. oz.) of clean water per gallon of coating.

AVERAGE DRY TIME@77ºF/25ºC (ASTM D 1640)
To touch: 1-2 hours Recoat: 2–4 hours (see Special Instructions)
Dry times and recoat times are temperature, humidty and film thickness dependent.

APPLICATION EQUIPMENT: Airless spray

AIRLESS SPRAY	BRUSH	ROLLER
PRESSURE: 1800-2500 psi **TIP:** .015"-.017"	Nylon/Polyester	Semi-Smooth Surfaces: ⅜" - ½" nap Rough Surfaces: ¾" - 1 ½" nap

PACKAGING: Quart, one-gallon, five-gallon containers

STORAGE: Store in a dry area. Protect from freezing. Protect from temperatures above 110ºF for extended periods of time. Extreme temperatures may cause paint to become unusable. See *Paint Storage Best Practices* Technical Bulletin at dunnedwards.com for more information.

CLEANUP: Warm, soapy water

DISPOSAL: For information on local options to dispose of unwanted left-over paint, call Dunn-Edwards Customer Service at 1-888-DEPAINT or visit www.dunnedwards.com. **Do not mix with other products.**

CONFORMS TO:	
• ARB 2007/2020 SCM & CALGreen 2022 • LEED v4/4.1 • SCAQMD Rule 1113 • CA Extended Producer Responsibility	• MIR, HPD • MPI Approved Product #6 • CRGI Green Wise Certified

SAFETY DATA SHEET: Available at www.dunnedwards.com

SURFACE PREPARATION: All surfaces must be cured, clean, dry, and free from dirt, dust, rust, stains, grease, oil, mildew, wax, efflorescence, bond-breakers, and other contaminants. Remove all loose, peeling, or chalky paint by sanding, scraping, or other appropriate methods. Repair all cracks, holes, and other surface imperfections with a suitable patching material. Repaired surfaces should then be sanded smooth and dusted clean. Glossy surfaces should be dulled to provide a roughened surface for good adhesion.

SPECIAL INSTRUCTIONS

- **CAUTION!** Scraping or sanding surfaces of older buildings (especially pre-1978) may release dust containing lead or asbestos. EXPOSURE TO LEAD OR ASBESTOS CAN BE VERY HAZARDOUS TO YOUR HEALTH. Wear a NIOSH-approved N100 particulate filter mask to avoid breathing dust. Use a HEPA vacuum for cleanup, and finish by water-washing all surfaces. For more information, see Dunn-Edwards brochure on "Surface Preparation Safety" or call U.S. EPA's lead hotline at 1-800-424-LEAD, or visit www.epa.gov/lead or / asbestos, or contact your state or local Health Agency.
- This product can neither cause nor prevent or cure the growth of mold, mildew, or other forms of fungus. Excessive moisture and inadequate ventilation are the main conditions that promote their growth. Correct any such conditions before painting.
- Exterior wood may be allowed to contain no more than 15% moisture. Painting over wood with excessively high moisture content can result in loss of adhesion, blistering, peeling, cracking, and discoloration.
- Apply two coats of **EZ-PRIME® Select (EZSL00)** on redwood and cedar in order to stop tannin bleeding. Allow first coat to dry for 24 hours before applying the second coat.
- Do not apply when the air or surface temperature is below 50ºF.

USE AS A PRIMER FOR

WOOD
Trim, sash, fascia:
Rough-sawn:
T1-11 siding:
Plywood:
} **EZ-PRIME® Select (EZSL00)**

SYNTHETIC WOOD
Masonite:
Hardboard:
MDO siding:
} **EZ-PRIME® Select (EZSL00)**

***This product has been tested and certified by Coatings Research Group Inc., an international paint industry-organized ISO-accredited testing laboratory, to meet performance and environmental standards as shown on www.greenwisepaint.com. Dunn-Edwards is a member of CRGI.*

HEALTH & SAFETY CAUTIONS! INHALATION OF SPRAY MIST OR SANDING DUST MAY BE HARMFUL. Use only with adequate ventilation. Avoid breathing vapors, spray mist and sanding dust. Wear NIOSH-approved N100 particulate filter mask when spraying or sanding. Avoid contact with skin and eyes. Do not ingest. Close container after each use. **FIRST AID:** If swallowed, immediately give 1 or 2 glasses of water to drink – for emergency information, call 1-800-222-1222. If having difficulty breathing, move to fresh air. For eye contact, immediately flush with water for 15 minutes. For skin contact, wash thoroughly with soap and water.

• KEEP OUT OF REACH OF CHILDREN •

Ingredient (CAS #): Water (7732-18-5); Copolymer Resin (Proprietary); Titanium Dioxide (13463-67-7); Aluminosilicates (68476-25-5/37244-96-5); Talc, Non-Asbestos (14807-96-6); Quartz (14808-60-7).

⚠ **WARNING:** Cancer and Reproductive Harm – www.P65Warnings.ca.gov

DUNN-EDWARDS CORPORATION • 520 S. 67th Ave, Phoenix, AZ 85043 USA • (888) DEPAINT® | dunnedwards.com
337-2468