



**PORCH & FLOOR
INT / EXT
100% ACRYLIC
3503 Series**

Type	Sheen	Spread Rate	Recommended Application	Thinner	Clean Up	DRY TIME		
						Tack Free	Re-coat	Cure
100% Acrylic	Semi - Gloss	350-400 Sq Ft Per Gallon	Brush, Roller, or Spray	Clean Water	Warm Soapy Water	30 Minutes	Over-night	7 - 10 Days
PRODUCT NAME: Porch & Floor Int / Ext 100% Acrylic Latex 3503 Series:		Porch & Floor Interior/Exterior Acrylic Floor Coating is designed for use on concrete or wood surfaces. It is water thinned so it poses no fire hazard or objectionable odor. The product is based on an acrylic resin that dries quickly to a tough, durable film that has excellent weather and abrasion resistance along with superior adhesion properties.						
WHERE TO USE:		For use on residential and light commercial porch and floor surfaces of concrete or wood. NOT FOR USE ON GARRAGE FLOORS. Ideal for basement floors, stairs, porches and patios. May also be used on vertical wood, metal and masonry surfaces.						
Surface Preparation:		The surface to be painted must be clean and free of dirt, chalk, mildew, wax, grease, rust or loose flaking paint. Mildew should be removed with a bleach and water solution and rinsed thoroughly. Wax should be removed by solvent cleaning. Grease and oil should be removed by using an oil and grease emulsifier. Rust must be removed by hand sanding vigorously or by conscientious power tool cleaning. Remove loose paint by scraping. Feather sand rough edges to insure a smooth finish coat. Glossy surfaces must be dulled by lightly sanding. Remove sanding dust before paint application. New concrete should be allowed to cure 30 days prior to painting. This product is self-priming on masonry and interior wood surfaces; prime exterior wood with 2090 Acrylic Bonding Primer, prime ferrous metal with 1220-111 Universal Metal Primer.						
Application:		Stir thoroughly before using. Use a quality nylon/polyester brush and 3/8" roller. Flow on generously working from the unpainted into the painted area while maintaining a wet edge. Clean equipment in warm soapy water. ALLOW 24 HOURS PRIOR TO LIGHT FOOT TRAFFIC, 72 HOURS BEFORE HEAVY USE. Do not apply below 10° C (50° F). Thin sparingly with water.						
NOTE: Formulated without mercury or lead.								

Resin:	100% Acrylic
Solids:	Volume – 36.0
Weight Per Gallon:	10.60 lbs.
Viscosity:	92 – 98 (Krebs Units)
Specular Gloss:	35 – 42 @ 60 degrees
Recommended Film Thickness:	Wet – 4.0 to 4.6 mils Dry – 1.45 to 1.65 mils
VOC – VOS Statement:	This product contains less than 100 grams per liter.
Cautions:	CAUTION! Do not take internally. Close container after each use. KEEP OUT OF REACH OF CHILDREN. KEEP FROM FREEZING.