GRIPCRETE MASONRY & PLASTER PRIMER 7166.10

Type	Sheen	Spread Rate	Recommended Application	Thinner	Clean Up	DRY TIME		
						Tack Free	Re-coat	Cure
Acrylic	Flat	200 Sq Ft Per Gallon	Brush, Roller or Airless Spray	Clean Water	Warm Soapy Water	1 Hour	4 Hours	7 Days

PRODUCT NAME: **7166.10 GRIPCRETE MASONRY & PLASTER PRIMER**	MASONRY & PLASTER PRIMER is specifically formulated to prime and seal masonry surfaces against alkali and efflorescence. Use on above-grade masonry and plaster surfaces to protect subsequent finishes from breakdown and burn-through caused by elevated pH levels. Minimize downtime and trade disruption by coating fresh masonry and plaster in as little as seven days.
WHERE TO USE:	MASONRY & PLASTER PRIMER is the ideal primer for interior and exterior smooth masonry surfaces. Protecting from alkali and efflorescence make it ideal for tilt-up and poured concreted, block, brick, stucco, EIFS, and plank siding. Tolerating pH levels of 7-13, allows for worry-free application to new, “hot” interior plaster.
SURFACE PREPARATION:	All new surfaces must cure for at least 7 days. Remove all form release and curing agents. For exterior concrete, pressure wash to remove all dirt, dust, grease, oil, loose particles, laitance, foreign material, peeling and defective coatings, chalks, etc. Allow the surface to dry before proceeding. Repair cracks, voids, and other holes with an appropriate patching compound or sealant. Concrete and mortar must be cured at least 7 days at 75°F. Moisture content must be 15% or lower. On tilt-up and poured-in-place concrete, commercial detergents and sandblasting may be necessary to remove sealers, release compounds, and to provide an anchor profile. Fill bugholes, air pockets and other voids with an acrylic elastomeric patch or sealant.
APPLICATION:	Mix thoroughly before use. Apply by brush, roller, or airless spray or conventional spray. If sprayed, product should be back-rolled or brushed to properly work into surface. Apply when the ambient, surface, and material temperatures 50° F or higher. DO NOT APPLY IN DIRECT SUNLIGHT. Thinning is not recommended. All products are formulated ready for application. If needed, thin sparingly and do not exceed 2oz per gallon. Clean all applicators with water immediately after use.
NOTE: Formulated without mercury or lead.	

Revised 03/2025

RESIN:	100% Acrylic
SOLIDS:	Weight – 50% Volume – 36%
WEIGHT PER GALLON:	10.65 lbs.
VISCOSITY:	105 (Krebs Units)
FLASH POINT:	200°F or over (TT-P-141, Method 4293)
SPECULAR GLOSS:	3 – 6% @ 60 Degrees
SAG RATING:	45/60+
RECOMMENDED FILM THICKNESS:	Dry – 2.9 mils
LIGHT REFLECTANCE:	N / A
VOC – VOS STATEMENT:	This product contains 50 grams per liter.
CAUTIONS:	**CAUTION!** Do not take internally. Close container after each use. **KEEP FROM FREEZING.** **KEEP OUT OF REACH OF CHILDREN.**

Revised 03/2025